

NATIONAL POOL FINISHES®

5-Year Warranty*

- 
- Upgrades KOOL DECK™ Surfaces
 - Painted or Unpainted Concrete Surfaces
 - Can Apply to Damp Surfaces
 - Cleans Up With Soap & Water
 - Cures Quickly
 - No Solvent Fumes
 - Back In Service In 2 Days
 - Excellent Color Retention

DECK KOTE™

The New Science
of Deck Coatings™
AGGREGATE
NON-SKID ADDITIVE

DECK KOTE™ - Acrylic Water-Based Deck Paint

A **Premium** one-part acrylic water-based deck coating designed as an effective weapon against UV rays and weathering in a coating that is easy to apply and clean up. Longest lasting protection against fade on painted or unpainted concrete surfaces. Dries quickly, durable, and resists fading, chemicals, and abrasion. Rejuvenates KOOL DECK™ and other textured deck surfaces. For non-skid surfaces, add sand or pumice stone as desired. Cleans up with soap and water. Designed for maximum protection against algae, UV rays and chlorine.

SUGGESTED USES: Painted or unpainted concrete surfaces.

COLORS: Available in 6601 Sand Buff, 6602 Adobe Buff, 6603 Aztec Gold, 6604 Aqua, 6605 Birch Gray, 6606 Rose Pink, 6607 Coral Peach, 6608 Sedona Tan, 6609 New England Blue, 6610 White

FINISH: Flat. For a non-skid finish, add pumice stone, sand or marble dust to paint as needed to achieve desired appearance.

VEHICLE TYPE: Acrylic Resin

SOLVENT TYPE: Water, Butyl Cellosolve, Diacetone Alcohol, Ethylene Glycol

VOC: 1.6 lbs. / gal (190 grams / liter)

FLASH POINT: Non Flammable

SOLIDS BY WEIGHT: 50%

WEIGHT PER GALLON: 11 lbs. per gallon (varies by color)

RECOMMENDED DRY FILM: 4.0 mils

COVERAGE: Theoretical coverage at two mils dry is 350 square feet per gallon, and recommended thickness of 4 mils dry would require 2 full coats. Material losses during mixing and application will vary and must be taken into consideration. Expect 50% less coverage on bare, rough or sandblasted surfaces.

VISCOSITY AT 75°F (24°C): 70-80 KU

AVERAGE DRY TIME 75°F: Dries to touch in 30 minutes. Can re-coat in 4 hours. Allow 2 days for complete cure before putting back in service.

RECOMMENDED REDUCER: Water

RECOMMENDED CLEAN UP: Soap & Water

RESISTANCE TO: Chlorine, Alkali, Algae, Mineral Oils, Fresh and Salt Water

RECOMMENDED PRIMERS: Self Priming

APPLICATION: Brush, Spray or Roller (preferred)

Roll: 3/8" nap mohair metal, lambskin, phenolic core roller. Keep roller wet. Roll in one direction, rewet, then cross roll.

Spray: Conventional Air 50 -70 psi, Tip Size .055 -.070, Airless 2200-2500 psi, Tip Size .019-.023.

SURFACE PREPARATION: Water blast the surface to remove all loose paint, dirt, oils and grease. Decks must be cleaned with a Tri-Sodium Phosphate (TSP) wash, scrubbing surface to get rid of oil, dirt and sun-tan lotions, and then etched with a 15-20% solution of muriatic acid. Then thoroughly rinse with TSP & flush with plenty of fresh water and allowed to dry thoroughly. Glossy surfaces should be power sanded to a 80 grit profile for proper adhesion.

POT LIFE: Not Applicable

LIMITATIONS: Do not apply if material, substrate or ambient temperature is below 50°F or above 95°F.

SHELF LIFE: Minimum 12 months

MIXING: Mechanically mix well for 10 minutes, apply as it comes from the container, and thin with water as needed for proper performance.

PACKAGE: 1 Gallon cans (2 per case), 5 gallon pails, 1 pint cans

Acrylic Resin
Diacetone Alcohol
Butyl Cellosolve
Ethylene Glycol
Titanium Dioxide
Talc
Calcium Carbonate

Proprietary
123-42-2
00111-76-2
107-21-1
13463-67-7
14807-96-6
1317-65-3

BLUE WATER MARINE PAINT
1999 ELIZABETH STREET, NORTH BRUNSWICK, N.J. 08902
(800) 628-8422
www.bluewatermarinepaint.com

This product contains a maximum of 1.6 pounds of VOS per gallon of coating. Maximum VOC content 190 grams/liter.